

AVOIDING Early Cracking

Cracks appearing in concrete within the first few hours after placing are either early-age shrinkage cracks, plastic shrinkage cracks or plastic settlement cracks, all of which form in the concrete prior to it gaining its final set.

CCAA Data Sheets on these topics give the reasons behind these forms of cracking. This Data Sheet summarises the recommendations for avoiding early cracking of concrete.



CRACKS appearing in concrete within the first few hours after placing are either early-age shrinkage cracks, plastic shrinkage cracks or plastic settlement cracks

DO

DO NOT

COMMENT

The Concrete

| | | |
|---|--|--|
| Order higher slump concrete if higher workability is required. | Do not add water to the concrete on site to improve workability. | Uncontrolled addition of water has undesirable effects on finishing and performance. |
| In very hot conditions, discuss concrete temperature with supplier and plan the pours appropriately. | Do not leave it to the last minute and delay placement. | High concrete temperature can have undesirable effects eg effects on setting. |

Preparation for Placing

| | | |
|---|---|---|
| Ensure uniform thickness of slab on ground | Do not place concrete on uneven ground. | Unevenness of the subgrade can be a source of crack initiation. |
| Use a layer of fine granular material or plastic membrane under slab on ground to reduce friction. | Do not neglect details required to reduce restraint to early age concrete movement. | Restraint by subgrade friction can lead to early cracking. |
| Dampen subgrade prior to placing concrete. | Do not place concrete on very dry ground. | Excessive moisture loss from concrete is undesirable. |
| Ensure that formwork is rigid prior to placing concrete. | Do not assume formwork can be adjusted during placing. | Formwork movement can cause settlement cracking. |
| Check weather conditions for the area. | Do not assume that because it is 'a nice day' the concrete will be unaffected. | To be prepared for likely adverse conditions is important. |
| Use evaporation charts (eg provided in CCAA Data Sheet on hot weather concreting). | Do not guess the rate of evaporation. | An accurate picture of the rate of evaporation is important. |
| Assess changes in drying conditions throughout the day. | Do not assume conditions in the afternoon will be the same as in the morning. | A breeze later in the day may be enough to cause cracking. |

Placing

| | | |
|--|---|--|
| Place concrete as soon as possible. | Do not place concrete more than 1½ hours after batching. | Placing concrete that has started to set may have undesirable effects. |
| Place concrete where required. | Do not move concrete horizontally using vibrators or drop from heights. | Segregation may occur and can have undesirable effects. |
| Delay slab placing for integral beam/slab or integral column/slab construction. | Do not pour such elements continuously. | Concrete in the deeper sections needs to settle for a short while before placing the slabs to avoid plastic settlement cracking. |
| Adequately compact the concrete. | Do not assume that screeding compacts the concrete. | Compaction removes entrapped air and improves the concrete's properties. |

Placing continues on page 3

DO

DO NOT

COMMENT

Placing *(continued)*

| | | |
|---|--|---|
| Thoroughly compact around inserts. | Do not neglect compaction because it may be difficult. | Anchorage of inserts is critical. |
| Close any early age cracking by re-compacting the concrete or re-trowelling the surface. | Do not leave re-compaction or re-trowelling too late. | Re-compaction must be prior to setting. Re-trowelling closes surface cracks and reduces risk of penetrating full depth. |

Early Protection and Curing

| | | |
|---|--|--|
| In windy conditions erect wind breaks or walls. | Do not work in windy conditions without protecting the concrete (although it may not always be practical). | Air movement over the surface can increase the rate of evaporation/ surface drying and risk of cracking. |
| Apply aliphatic alcohol immediately after screeding and bullfloating. | Do not wait until after the water sheen has gone from the surface. | Use of aliphatic alcohol slows the rate of surface drying In the first few hours. |
| Re-apply aliphatic alcohol to surfaces after each finishing operation. | Do not apply aliphatic alcohol if the water sheen has gone from the surface. | Finishing operations break up the film formed by the early application so reapplication is necessary. |
| Apply aliphatic alcohol to low-bleed concrete in all weather conditions. | Do not assume that mild drying conditions will not cause cracking. | Low-bleed concrete is prone to early cracking even in mild conditions. |
| Spray surfaces with a fog spray of water. | Do not allow the surface to dry. Do not use normal hose (damage to the surface may result). | An alternative method to aliphatic alcohol to slow down the rate of surface drying. |
| Cure the concrete. Use: Water ponding Continuously damp hessian Impervious sheets Membrane forming curing compounds | Do not leave it to 'Air Cure'. Do not let surface dry between applications of water. Do not wait or apply curing compounds the next day. | 'Air Curing' is merely drying and must be avoided. Effective curing system must be used. Curing should keep the maximum amount of water in the concrete. |
| Start the curing early. | Do not leave it until tomorrow; tomorrow is always too late. | Curing should commence as soon as finishing is complete. |
| Ensure that all joints are in place early. Provide saw-cut joints as soon as the concrete has hardened sufficiently. | Do not delay saw-cut joints. | Joints are necessary to provide crack control as the concrete dries and shrinks. |

JUNE
2005

FURTHER INFORMATION:

CCAA Datasheets

Plastic Shrinkage Cracking
Plastic Settlement Cracking
Early Age Shrinkage Cracking
Hot Weather Concreting
Download from www.concrete.net.au.

CCAA Guide to Concrete Construction (T41/HB64)
Cement and Concrete Association of Australia and
Standards Australia, 2002.

CCAA OFFICES

SYDNEY OFFICE:

Level 6, 504 Pacific Highway
St Leonards NSW Australia 2065

POSTAL ADDRESS:

Locked Bag 2010
St Leonards NSW 1590

TELEPHONE: (61 2) 9437 9711

FACSIMILE: (61 2) 9437 9470

BRISBANE OFFICE:

Level 14, IBM Building
348 Edward Street
Brisbane QLD 4000

TELEPHONE: (61 7) 3831 3288

FACSIMILE: (61 7) 3839 6005

MELBOURNE OFFICE:

2nd Floor, 1 Hobson Street
South Yarra VIC 3141

TELEPHONE: (61 3) 9825 0200

FACSIMILE: (61 3) 9825 0222

PERTH OFFICE:

45 Ventnor Avenue
West Perth WA 6005

TELEPHONE: (61 8) 9389 4452

FACSIMILE: (61 8) 9389 4451

ADELAIDE OFFICE:

Greenhill Executive Suites
213 Greenhill Road
Eastwood SA 5063

POSTAL ADDRESS:

PO Box 229
Fullarton SA 5063

TELEPHONE: (61 8) 8274 3758

FACSIMILE: (61 8) 8373 7210

EXTRACTIVE INDUSTRIES OFFICE

PO Box 243

Henley Beach SA 5022

TELEPHONE: (61 8) 8353 8151

FACSIMILE: (61 8) 8353 8151

TASMANIAN OFFICE:

EXTRACTIVE INDUSTRIES OFFICE

PO Box 246

Sheffield TAS 7306

TELEPHONE: (61 3) 6491 2529

FACSIMILE: (61 3) 6491 2529

WEBSITE: www.concrete.net.au

EMAIL: info@ccaa.com.au

LAYOUT: Helen Rix Design

Disclaimer: Cement Concrete & Aggregates Australia is a not for profit organisation sponsored by the cement concrete and aggregate industries in Australia to provide information on the many uses of cement and concrete. This publication is produced by CCAA for that purpose. Since the information provided is intended for general guidance only and in no way replaces the services of professional consultants on particular projects, no legal liability can be accepted by CCAA for its use.

CCAA respects your privacy. Your details have been collected to provide you with information on our activities, publications and services. From time to time your details may be made available to third party organisations who comply with the Privacy Act such as affiliated associations, sponsors of events and other reputable organisations whose services we think you may find of interest. If you do not wish to receive information from CCAA or wish to be taken off the database please write to the Privacy Officer, CCAA, Locked Bag 2010, St Leonards, NSW, 1590